

## MOTIP NC-Combi Finishing Putty

Ord.-no.: 000063

### Technical Information



Level small, superficial irregularities in surfaces of steel, aluminium, wood and polyester on your car with fast drying MOTIP Finishing Putty. Finishing putty has a fine structure and is easy to sand. MOTIP Finishing putty is re-sprayable with all lacquer systems and can be applied in layers up to 0.5 mm.

#### Quality & properties

- Easy to sand
- Fast drying
- Re-sprayable with all lacquer systems
- Very fine structure
- Excellent adhesion

#### Physical & chemical data

- Colourname: olive green
- Smell: Characteristic
- Degree of gloss: mat, 10 ±2 GU
- Sandable: 2-3 h
- Vapour pressure: 13/20
- Flash point: 27 °C
- Relative density: 1.43 g/cm<sup>3</sup>
- Storage stability: 24 m
- Content: 250 G

#### How to use

- Before use, carefully read the directions on the packaging and act accordingly.
- Processing temperature 15 – 25°C.
- The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.
- Apply the finishing putty in the desired layer thickness with an applicator.
- The drying time depends on the ambient temperature.
- After use, directly clean the tools used.

#### Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

#### Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

#### Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

For any further technical questions call our hotline +31 (0) 561 69 44 00 from Monday to Thursday from 9 h a.m. to 3 h p.m. or on Friday until 12 h p.m.

**As of June 2, 2023** – This release replaces all eventually earlier issued versions.