

MOTIP Plastic Repair Putty

Ord.-no.: 000059

Technical Information



Level irregularities on different plastic surfaces, with exception of polyethylene (PE) and polypropylene (PP) of your car with MOTIP 2-component Plastic Repair Putty. Also suitable for surfaces of steel, aluminium, wood, concrete and polyester, which are subject to vibrations. Plastic repair putty is very elastic and easy to sand. Plastic repair putty can be resprayed with all paints, also powder coating, and has a very fine structure. Plastic repair putty is resistant to chemicals and the weather and has excellent adhesion. MOTIP Plastic Repair Putty can be applied in layers with a thickness up to 1 centimetre.

Quality & properties

- Easy to sand
- Very elastic
- Re-sprayable with all lacquer systems, also powder coating
- Very fine structure
- Resistant to chemicals and weather influences
- Excellent adhesion

Physical & chemical data

- Base: Polyester resin
- Colourname: grey
- Smell: Characteristic
- Degree of gloss: mat, 10 ±2
- Completely dry: 60 min
- Overcoatable: 60 min
- Sandable: 30 min
- Surfaces: Steel, aluminium, wood, concrete, polyester
- Minimum Working Temperature: 10 °C
- Maximum Working Temperature: 25 °C
- Relative density: 0.85 g/ml
- Pot life: 3-5 min
- Addition of hardener: 2.5 %
- Storage stability: 1.5 y
- Content: 420 G

How to use

- Before use, carefully read the directions on the packaging and act accordingly.
- Processing temperature 15 – 25°C.
- The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.
- Mix the required amount of putty with the harder. Apply in the desired layer thickness.
- After hardening, sand and when desired apply a fine putty.
- The drying time depends on the ambient temperature.
- After use, directly clean the tools used. Do not store the surplus material, mixed with harder, in the can.

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labeling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

For any further technical questions call our hotline +31 (0) 561 69 44 00 from Monday to Thursday from 9 h a.m. to 3 h p.m. or on Friday until 12 h p.m.

As of August 17, 2022 – This release replaces all eventually earlier issued versions.

