

Product name	:	MoTip Lacquer, black		
Gloss 500 ml	:	Satin Matt	High gloss	Matt
Article number	:	04001	04005	04006
Gloss 150 ml	:	High gloss	Matt	
Article number	:	00105	00106	

Supplier / Producer	:	MOTIP DUPLI B.V.		
		Wolframweg 2		
		NL-8471 XC WOLVEGA		
		Telephone number		+31 561 – 69 44 00
		Telefax number		+31 561 – 69 44 31

## Product description

High quality, fast-drying lacquer to treat surfaces, treated and untreated, of wood, metal, aluminium, glass, stone and various types of plastic.

## Product characteristics

Fast drying  
Good coverage  
Lasting gloss  
Non-fading and UV resistant  
Good surface hardness  
Resistant to petrol, chemicals and weather influences  
Wear resistant and scratch free  
Excellent adhesion

## Physical and Chemical Characteristics

Contents	:	500 ml	150 ml
Base	:	Acrylic resin	
Colour	:	Black	
VOC-content	:	Approximately 91% w/w	
Solid Content	:	Approximately 9% w/w	
Coverage	:	1,5 to 2 m <sup>2</sup>	Approximately 0,5 m <sup>2</sup>
Dust dry	:	After 5 to 10 minutes	
Tack free	:	After 10 to 20 minutes	
Hardened/re-sprayable	:	After 2 hours	
Heat resistant	:	To 110°C	

## Usage

**Before use, carefully read the directions on the packaging and act accordingly.**

### Pre Treatment

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface. Apply a layer of MoTip primer suitable for the surface. After drying, sand the base layer (grain 600).

### Treat

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

**The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.**